

SPORT COURTS SYSTEM

BASIC Solution

Aesthetic multilayer treatment for concrete and asphalt pavements.

ADVANTAGES

- › Approx. Thickness: 2-3 mm
- › Granulated anti-slipping texture
- › Easy application.
- › Outstanding durability
- › Outstanding adhesion to substrates.
- › UV-light resistant
- › Available in a wide range of colors.

APPLICATIONS

- › Sport pavements (tennis, basketball courts etc.).

SYSTEM

Products:

- › POLIPRIMER: Water-based acrylic primer.
- › ROADSEAL SYNTHETIC: Grout-like mixture consisting of controlled size sand and gravel in a synthetic resin matrix.
- › ROADSEAL SPORT: Grout-like mixture consisting of controlled fine size sand and gravel in a synthetic resin matrix.
- › PINTURACRILIC (optional): Water-based acrylic Paint containing acrylic-styrenated resins.

STRUCTURE OF THE SYSTEM

- › A priming Poliprimer layer, approx. dosage 0,3 kg/m² (depending on the substrate type)
- › A Roadseal Synthetic layer, approx. dosage 1-1.5 kg/m²
- › A Roadseal Sport layer, approx. dosage 0,8 – 1 kg/m²
- › A Pinturacrilic layer (optional), approx. dosage 0,5 kg/m² when a less texturized finishing is desired.

SPORT COURTS SYSTEM

BASIC Solution

PERFORMANCE CHARACTERISTICS

- Wearing resistance: The high acrylic resin contain of the system provides it with high outdoor weathering resistance and good resistance in light traffic conditions. Wearing resistance test UNE-EN 12274-5 < 500 (g/m²).
- Anti-slipping behavior: Class 3 (Rd > 45) according to the pendulum test in UNE-ENV 12633:2003 Annex A standard.

INSTRUCTIONS FOR USE

- Make sure that the substrate is clean, free of dust, humidity and other substances (oil, lime, etc.). The Surface to be primed must be cohesive.
- When using the system on hydraulic concrete, the Surface must be analyze in order to prevent adhesion problems due to excessive polishing, meteorization, humidity, etc. Application in the range 10-35°C is recommended. It is not recommended to apply the system under adverse weather conditions.
- Gently homogenize the products in the container before application. Use a rubber scrap or any other appropriate method to apply a uniform layer and let it dry completely before applying a subsequent layer (24 hours approx, depending on environmental temperature and humidity).
- NEVER add water directly to the products. Adding water would induce the loss of cohesion properties.
- Working tools can be cleaned with water while the product is not dry.

