

# CEPSASFALT FUEL RM

## DEFINITION:

Asphalt binder with improved resistance to fuels (gasoline and diesel).

## SPECIFICATIONS:

Characteristics	Units	Standard	Min.	Max.
<b>Original binder</b>				
Penetration (25 °C; 100 g; 5s)	0,1 mm	EN 1426	25	35
Softening point	°C	EN 1427	70	
Flash point	°C	EN 2592	240	-
<b>RTFOT residue</b>				
Mass variation	%	EN 12607-1	-	0,5
Penetration (25 °C; 100 g; 5 s)	% p.o.	EN 1426	53	-
Variation in softening point	°C	EN 1427	-	11

## APPLICATIONS:

→ Bituminous mixtures in which a better resistance to gasoline and diesel is required.

## RECOMMENDED WORKING TEMPERATURES:

- Mixing temperature (°C): 150-160.
- Working temperature (°C): 150-160.
- Compaction temperature (°C): 145-15.
- Maximum heating temperature (°C): 170.