

DISPRIMER

DEFINITION:

Asphalt paint consisting of modified bitumen and aromatic solvents, which provides excellent protection for all surfaces.

SPECIFICATIONS:

Characteristics	Unit	Standard	Min.	Max.
Brookfield viscosity at 25°C	mPa.s	NIE-008	100	300
Inflammability	°C	UNE 104281-1.12	25	-
Density at 25°C		UNE 104281-5.4	0,92	0,96
Non – volatile material	%	UNE 104281-3.7	48	52
Volatile organic compounds	g/l	ISO 11890-1	-	500
Characteristics of the residue				
Dry to touch at 25°C and 50% Hr	h	UNE 104281-5.13	-	1
Dry for repainting at 25°C and 60% Hr	h	UNE 104281-5.13	-	24

APPLICATIONS:

- Priming surfaces for subsequent waterproofing.
- Protection of metallic structures.
- Superficial waterproof protection for buried concrete elements.
- Protection of buried concrete elements.

PROPERTIES:

- Easy to apply.
- Easy to handle.

Revision nº2 - Approved: 01/02/2023 – Next revision: 01/02/2028

For further information visit www.cepsa.com

N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Cepsa takes no responsibility whatsoever for misuse. For individual cases, contact Cepsa' Technical Department.

- Good adherence to the substrates.
- Inflammable.

INSTRUCTIONS FOR USE:

- The support upon which Disprimer is to be applied should have a clean, adherent surface free of dust and other substances (oils, lime, etc.) which might affect adherence or reduce the product's properties. It is advisable to sandblast the support to clean it.
- Mix the product in its container before applying it.
- Apply with a spray gun, brush or roller.
- Let each coat dry before applying the next coat.

STORAGE:

- The containers should be kept somewhere where they are protected from both frost and overexposure to the sun.
- Storage temperatures should not be below 5°C since this could affect the quality of the product.
- After use, tightly seal the containers to prevent evaporation of the solvent and the corresponding increase in the viscosity of the paint.
- Keep away from fire.
- The maximum storage time recommended is 12 months from the manufacturing date in the original containers, undamaged and tightly closed.

OTHER RECOMMENDATIONS:

- The product should be applied at temperatures of between 5°C-35°C and should not be applied in bad weather.
- Since the paint contains solvents, it should be applied in ventilated places using EPIs.
- If necessary, solvents can be added to thin it.
- The area treated should be protected from direct sunlight.
- Disprimer is not suitable for applications where it would be in contact with solvents or fuels.