

EMULSIONS - SURFACE DRESSINGS

EMASFALT TRG-2 EXPORT (C65B2 TRG)

DEFINITION:

Fast setting cationic bituminous emulsion with a good storage performance and for long transportation distances, which complies with specifications contained in EN 13808:2013 for a C65B2 type emulsion.

SPECIFICATIONS:

Characteristics	Units	Standard	Min.	Max.
Properties of the emulsion				
Particle polarity	-	EN 1430	Positive	
Breaking value (Forshammer filler)	-	EN 13075-1	-	110
Efflux time (4 mm, 40 °C) (*)	S	EN 12846-1	5	70
Binder content (per water content)	%	EN 1428	63	67
Oil distillate content	%	EN 1431		2
Residue on sieving (0,5 mm sieve)	%	EN 1429	-	0,10
Settling tendency (7 days storage)	%	EN 12847	-	5
Water effect on binder adhesion	%	EN 13614	90	-
Residual binder		EN 1431		
Penetration (25 °C)	0,1 mm	EN 1426		220
Softening Point	°C	EN 1427	35	-
Recovered binder		EN 13074-1		
Penetration (25 °C)	0,1 mm	EN 1426	·	330
Softening Point	°C	EN 1427	35	-
Stabilised binder		EN 13704-2		
Penetration (25 °C)	0,1 mm	EN 1426	-	220
Softening Point	°C	EN 1427	35	-

(*) Efflux time between 40 – 130 s it is allowed for 2 mm according to the characteristics of the materials.



For further information visit www.cepsa.com

Revision nº1 - Approved: 01/02/2023 - Next revision: 01/02/2028

N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Cepsa takes no responsibility whatsoever for misuse. For individual cases, contact Cepsa' Technical Department.



EMULSIONS – SURFACE DRESSINGS

APPLICATIONS:

→ Surface dressings.

RECOMMENDED WORKING TEMPERATURES:

→ Application temperature (°C): 30-60. Within this range, heating the emulsion is not necessary for its application but, If the emulsion must be heated, special care must be taken to not exceed the 60°C limit. In this case, it is recommended to carry out the heating with means that guarantee correct temperature control and its homogeneity throughout the emulsion, avoiding specific overheating that could damage the product.

RECOMMENDED DOSAGE:

→ Depending on the type of treatment and the chipping size, the dosage will be different. For application using two layers, the residual binder dosage will vary around 1.3 – 2.2 g/m² between them.

GENERAL RECOMMENDATIONS:

- \rightarrow Cleaning the support and the chippings.
- → It is recommended to use the specified chipping shape.
- → Appropriate equipment, with clean injectors for a proper and homogeneous dosage throughout the support, avoiding spear irrigation.
- \rightarrow Allows storage for up to 60 days.



For further information visit www.cepsa.com