

# IMPRIMUL

## DEFINITION:

Non-ionic water soluble bituminous priming emulsion suitable for protecting/preserving surfaces.

## SPECIFICATIONS:

Characteristics	Unit	Standard	Min.	Max.
<b>Emulsión Original</b>				
Relative density at 25°C	-	UNE 104281-3.5	0,98	1,12
Water content	%	UNE 104281-3.2	56	64
Ash content	%	UNE 104281-3.8	25	40
Hardening	-	UNE 104281-3.9	Less than 24 hours after application	
Volatile organic compounds	g/l	ASTM D2369	-	30

## APPLICATIONS:

→ Priming for flooring and walls before application of asphalt-based products.

## PROPERTIES:

- Easy to apply.
- Easy to handle.
- Good adherence to the substrates.
- Resistant to alkalinity of cement.
- High penetration in the substrate when used as primer.
- VOCs free.

Revision nº2 - Approved: 01/02/2023 – Next revision: 01/02/2028

For further information visit [www.cepsa.com](http://www.cepsa.com)

N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Cepsa takes no responsibility whatsoever for misuse. For individual cases, contact Cepsa' Technical Department.

## INSTRUCTIONS FOR USE:

- Imprimul should be applied on clean surfaces. Presence of dust, oil, lime, or any other pollutant may reduce adherence and detriment Imprimul's properties. For an optimum performance of the product follow the next steps:
  - Mix the emulsion vigorously in the container before applying it.
  - Use as primer a 25% solution of Imprimul in water (one part of product in three of water). Let it dry completely before applying the product.
  - Apply Imprimul using a roller or any other suitable tool. Let the first layer dry completely before applying the next one (about 24 hours depending on the environmental humidity and ambient temperature).

## RECOMMENDED DOSAGE:

- The coverage rate is determined by the type of application and range between 250 y 500 g/m<sup>2</sup> of the neat product.

## STORAGE:

- The containers should be protected from both frost and overexposure to the sun.
- Storage temperatures should no be below 5°C since it could affect the quality of the product.
- Close tightly the containers after using to prevent evaporation of water.

## OTHER RECOMMENDATIONS:

- The product should be applied at temperatures between 10°C – 35°C, avoiding unstable weather conditions.
- For Imprimul application indoors, the place should be well ventilated to favor correct curing.
- Imprimul is not suitable for applications in contact with solvents or fuels.
- The treated surface should be protected against direct sunlight.
- For cleaning tools and equipment, water can be used before the product dries. After that, they can be cleaned with any industrial solvent.