

CONSTRUCTION - MULTILAYER SYSTEMS

# SPORT COURT SYSTEM

#### **DEFINITION:**

Aesthetic multilayer treatment for concrete and asphalt pavements. Specifically designed for indoor sports applications.

# **APPLICATIONS:**

→ Indoor sport pavements (tennis, basketball courts, etc.)

# **ADVANTAGES**:

- $\rightarrow$  Approx. thickness: 2 3 mm.
- → Granulated anti-slipping texture
- → Easy application.
- → Outstanding durability.
- → Outstanding adhesion to substrates.
- → Available in a wide range of colors.

### SYSTEM:

- → POLIPRIMER: water-based acrylic primer.
- → ROADSEAL ASPHALT: grout-like mixture consisting of controlled size sand and gravel and a high stability bituminous emulsion.
- → ROADSEAL SPORT: grout-like mixture consisting of controlled fine size sand and gravel in a synthetic resin matrix.
- → PINTURACRILIC (optional): Water-based acrylic paint containing acrylic-styrenated resins.



Revision  $n^{\circ}2$  - Approved: 01/02/2023 – Next revision: 01/02/2028

For further information visit www.cepsa.com



CONSTRUCTION - MULTILAYER SYSTEMS

# STRUCTURE OF THE SYSTEM:

- $\rightarrow$  A priming Poliprimer layer, approx. dosage 0,3 kg/m<sup>2</sup> (depending on the substrate type).
- → A Roadseal Asphalt layer, approx. dosage 1.5-2 kg/m<sup>2</sup>.
- $\rightarrow$  Two Roadseal Sport layer, approx. dosage 0,8 1 kg/m<sup>2</sup> each.
- → A Pinturacrilic layer (optional), approx. dosage 0.3 kg/m<sup>3</sup> if a less texturized finishing is required.

# **INSTRUCTIONS FOR USE:**

- → Make sure that the substrate is clean, free of dust, humidity, and other substances (oil, lime, etc.). The surface to be primed must be cohesive.
- → When using the system on hydraulic concrete, the Surface must be analyzed to prevent adhesion problems due to excessive polishing, meteorization, humidity, etc. Application in the range 10-35°C is recommended. It is not recommended to apply the system under adverse weather conditions.
- → Gently homogenize the products in the container before application. Use a rubber scrap or any other appropriate method to apply a uniform layer and let it dry completely before applying a subsequent layer (24 hours approx., depending on environmental temperature and humidity).
- → NEVER add water directly to the products. Adding water would induce the loss of cohesion properties.
- $\rightarrow$  Working tools can be cleaned with water while the product is not dry.

# PERFORMANCE CHARACTERISTICS:


- → Wearing resistance: The high acrylic resin contain of the system provides it with high outdoor weathering resistance and good resistance in light traffic conditions. Wearing resistance test UNE-EN 12274-5 < 350 (g/m<sup>2</sup>).
- → Anti-slipping behavior: Class 3 (Rd > 45) according to the pendulum test in UNE-ENV 12633:2003 Annex A standard.



ASPHALTS



#### CONSTRUCTION - MULTILAYER SYSTEMS



AENOR Empresa References Net N ISO 3001 Revision n°2 - Approved: 01/02/2023 - Next revision: 01/02/2028

For further information visit www.cepsa.com

N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Cepsa takes no responsibility whatsoever for misuse. For individual cases, contact Cepsa' Technical Department.