

INDUSFALT 70/40

Asphaltic bitumen obtained by direct distillation or other refining methods containing rheology modifiers specifically designed to be used as base in industrial products.

SPECIFICATIONS

Características	Unidad	Norma	Min.	Máx.
Softening point (R&B)	°C	EN 1427	65	75
Penetration (25°C, 100g, 5s)	0,1 mm	EN 1426	35	45
Solubility in xylene	%	EN 12592	99	--
Mass loss	%	EN 13303	--	0,5
Flash point	°C	EN ISO 2592	250	--

RECOMMENDED WORKING TEMPERATURES

> 110 - 160°C.

APPLICATIONS

> Raw material for waterproofing products in construction and membranes, joint sealing compounds and asphaltic paints.